



Technical Data Sheet



Guaranteed Values

High-speed Inkjet paper

Brand:

KomiJet

Parameters	Unit of measure	Test method	Substance (g/m ²)			
			65	75	80	100
Basis weight	g/m ²	ISO 536	65 ±2	75 ±3	80 ±3	100 ±4
Caliper	mkm	ISO 534	85 ±4	100 ±4	104 ±3	126 ±5
Opacity, min	%	ISO 2471	84	91	91	91
Breaking length MD, min	m	ISO 1924	4500			
Roughness Bendtsen	ml/min	ISO 8791	no more 320	no more 350	no more 350	no more 320
CIE whiteness		ISO 11475	145 ±3	143 ±3	146 ±3	145 ±3
Cobb 60	g/m ²	ISO 535	34 ±11	no more 70	45 ±25	34 ±11
Moisture	%	ISO 287	4.5 - 7.0	4.6 ±0.6	4.6 ±0.6	4.5 - 7.0

Information:

Mill's certificates

- ISO 9001
- ISO 14001
- ISO 45001

Test conditions: Guaranteed values after conditioning, measured at 50 ± 2% RH and 23 ± 1°C (ISO 187:1990)

System for verifying legal origin of the wood for this product complies with international standard ISO 38200:2018 Chain of custody of wood and wood based products and Forest Certification Legal Origin standard

ECF technology (Elemental Chlorine Free)

Product description:

Uncoated fine paper in reels designed for High-speed Inkjet printing machines