



## Technical Data Sheet



### Guaranteed Values

Printing paper

Brand:

KomiText

Parameter	Unit	Test method	Substance
			45
1. Basis weight	g/m <sup>2</sup>	ISO 536	45,0 +1,0/-1,5
23. Density	g/cm <sup>3</sup>	ISO 534	min 0,60
18.19.Smoothness	sec	ISO 5627	80-200
12.Average breaking length MD and CD	m	ISO 1924	min 2500
44.Moisture	%	ISO 287	7,0-9,0
225.Brightness D65/10	%	ISO 2470	min 65
427.Dirt spots 0,1-0,5 mm <sup>2</sup>	p.	GOST 13525,4	max 200

### Information:

Mill's certificates

- ISO 9001
- ISO 14001
- ISO 45001

Test conditions: Guaranteed values after conditioning measured at 50 ± 2% RH and 23 ± 1°C (ISO 187:1990)

System for verifying legal origin of the wood for this product complies with international standard ISO 38200:2018 Chain of custody of wood and wood based products and Forest Certification Legal Origin standard

Product description:

Uncoated mechanical paper without recycled fiber.

Valid until: 31.12.2025 or until further notice